


<b>CR-718</b>	<b>LOW HYDROGEN - IRON POWDER ELECTRODE FOR WELDING DEOXIDISED C-Mn STEELS WITH HIGHER SUB-ZERO TOUGHNESS PROPERTIES</b>				<b>DATA SHEET NO. 24</b>						
	SPECIFICATION	AWS A5.1	BS EN ISO 2560-B	JIS Z 3212							
CLASSIFICATION	E7018	E4918	D5016								
PRODUCT DESCRIPTION	<p>The design emphasis of the chemically basic flux is engineered to ensure the optimum weld metal properties demanded by the specification are fully met.</p> <p>The basic flux containing the appropriate alloying elements with a controlled balanced addition of iron powder is extruded onto a high purity ferritic core wire with a blend of silicates that ensures both coating strength and a coating resistant to subsequent moisture absorption.</p>										
WELDING FEATURES OF THE ELECTRODE	<p>The chemical nature of the flux together with a significant proportion of iron powder ensures maximum deposition efficiency without detracting from its ability to be used in all positions except vertical down.</p> <p>Overall the arc is very stable, slag detachability is good and metal recovery is some 115% with respect to the core wire. <b>UNCONTROLLED</b></p>										
APPLICATIONS AND MATERIALS TO BE WELDED	<p>As with RD-718 it is suitable for all grades <del>of C-Mn structural steels</del>. However, it is used to best advantage on fully deoxidised C-Mn steels when high toughness values are specified down to -45°C.</p> <p>These toughness properties are maintained even after extended PWHT making it ideal for pressure vessel work. The low weld Si and high Mn to Si ratio ensure maximum resistance to solidification cracking on thick restrained sections.</p>										
WELD METAL ANALYSIS COMPOSITION % BY Wt.		C	Mn	Si	S	P	Cr	Ni	Mo	V	Fe
	MIN	-	-	-	-	-	-	-	-	-	-
	MAX	0.15	1.6	0.75	0.035	0.035	0.2	0.3	0.3	0.08	
	TYPICAL	0.06	1.4	0.35	0.01	0.02	0.05	0.06	0.03	0.02	Bal.
WELD METAL PROPERTIES (ALL WELD METAL)	<u>PROPERTY</u>	<u>UNITS</u>	<u>MINIMUM</u>	<u>TYPICAL</u>	<u>OTHERS</u>						
	Tensile strength	N/mm <sup>2</sup>	490	600							
	0.2% Proof stress	N/mm <sup>2</sup>	400	500							
	Elongation on 4d	%	22	28							
	Reduction of Area (RA)	%	-	70							
	Impact energy -30 °C	J	27	100							
WELDING AMPERAGE AC or DC+	Ø mm)	2.6	3.2	4.0	5.0						
	MIN	50	75	130	180						
	MAX	85	125	170	220						
OTHER DATA	Electrodes that have become damp should be re-dried at 150°C for 1 hour.										
RELATED PRODUCTS	Please contact our Technical Department for detail.										